

Georgia Pacific

SBS COATED ONE SIDE CROSSET, ARKANSAS MILL

Gsm (nominal)	236	264	278	293	309	322	353	381	407
Lbs / 3MSF (nominal)	145	162	171	180	190	198	217	234	250
um	305	356	381	406	432	457	508	559	610
inches	.012	.014	.015	.016	.017	.018	.020	.022	.024
ISO brightness	84	84	84	84	84	84	84	84	84
Sheffield smoothness	25	28	31	34	37	40	45	50	55
ZDt	32	32	32	32	32	32	32	32	32
Hunter color “b”	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5
Stiffness MD	85	150	170	200	230	260	340	430	520
Stiffness CD	40	70	85	95	110	135	170	215	255
Percent moisture	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0
Grade code	FC2145	FC2162	FC2171	FC2180	FC2190	FC2198	FC2217	FC2234	FC2250